

Phases of the 2D Hubbard model at low doping

Andrey V. Chubukov, Karen A. Musaelian

Department of Physics, University of Wisconsin - Madison, 1150 University Avenue, Madison,

WI 53706

(February 1, 2008)

Abstract

We show that the planar spiral phase of the 2D Hubbard model at low doping, x , is unstable towards a noncoplanar spin configuration. The novel equilibrium state we found at low doping is incommensurate with the inverse pitch of the spiral varying as $\sqrt{x}$, but nevertheless has a dominant peak in the susceptibility at (π, π) . Relevance to the NMR and neutron scattering experiments in $La_{2-x}Sr_xCuO_4$ is discussed.

Magnetic properties of the CuO_2 layers in the high temperature superconductors have been recently attracting an intense interest [1] as magnetism is possibly a major contributor to the mechanism of superconductivity. Among cuprate superconductors, La_2CuO_4 holds a special place as the most simple and extensively experimentally studied compound. There are numerous reasons to believe that magnetic properties of $La_{2-x}Sr_xCuO_4$ are quantitatively captured by the 2D Hubbard model with chiefly the nearest-neighbor hopping

$$\mathcal{H} = -t \sum_{i,j} a_{i,\alpha}^\dagger a_{j,\alpha} + U \sum_i n_{i,\uparrow} n_{i,\downarrow} \quad (1)$$

Here α is a spin index, and $n = a^\dagger a$. At half-filling, the ground state of the 2D Hubbard model exhibits a long range commensurate Néel order. However, the introduction of even a very small number of holes into the system brings about a dramatic change in the nature of the ground state as the $T = 0$ static Pauli susceptibility associated with vacancies does not depend on the carrier concentration in two spatial dimensions.

Shraiman and Siggia pointed out [2] that holes introduced into a commensurate antiferromagnet give rise to a long-range dipolar distortion of the staggered magnetization. In the simplest scenario, this leads to a spiral spin configuration with the momentum (π, Q) . The incommensurate (π, Q) spin-density-wave phase was also obtained in the early perturbative studies of the Hubbard model with small U [3] and in several other mean-field [4,5] and self-consistent [6] calculations. Experimental situation in $La_{2-x}Sr_xCuO_4$ is however far from being clear. On one hand, the inelastic neutron scattering experiments [7] have shown that χ'' is peaked at incommensurate (π, Q) and symmetry related wave vectors, with Q varying as $\pi - Q \approx 2\pi x$. On the other hand, the longitudinal spin-lattice relaxation rate data for ^{17}O [8], obtained at far smaller frequencies cannot be fitted by the form of χ'' inferred from the neutron scattering experiments.

In this communication we use the RPA formalism of Schrieffer, Wen and Zhang [9] and study in detail the structure of magnetic correlations in the Hubbard model at small doping. We will show on the basis of an analysis of low frequency bosonic modes that the (π, Q) spiral state is actually *unstable* with respect to a more complex *noncoplanar*

spin configuration which, though incommensurate, has a dominant peak in the dynamical susceptibility precisely at (π, π) .

The analysis presented here is related to other works on incommensurate magnetic phases at finite doping. Previous mean-field studies of the Hubbard and $t - J$ models [2,4,5] have shown that in a certain range of parameters, the (π, Q) spiral state has lower energy than both the Néel state and the spiral state with the pitch in both spatial directions. Our energy analysis is consistent with their results. Shraiman and Siggia [10] developed a macroscopic theory of the bosonic excitations in the spiral phase. To the lowest order in density, they found a peculiar degeneracy in the ground state energy for the planar spiral state and for a whole set of noncoplanar magnetic configurations with the plane of the spiral varying in space. This degeneracy is also present in our microscopic calculations. However, the further assumption of Shraiman and Siggia that the next-order terms in doping concentration stabilize the planar spiral state is inconsistent with our microscopic results for the Hubbard model.

As an input for our analysis, we will need an expression for the energy spectrum, E_k , of a single hole in a quantum antiferromagnet. The mean-field theory gives $E_k = -\sqrt{\epsilon_k^2 + \Delta^2}$, where $\epsilon_k = -2t(\cos k_x + \cos k_y)$ and Δ is a gap which separates valence and conduction bands [4,11,9,12]. This energy is obviously degenerate along the whole edge of the magnetic Brillouin zone $|k_x \pm k_y| = \pi$, where E_k has a maximum. However, both perturbative [13] and variational [14] studies have shown that this degeneracy does not survive the effects of quantum fluctuations, and the actual dispersion has a maximum at four points $(\pm\pi/2, \pm\pi/2)$ in the center of each of the edges of the magnetic Brillouin zone. In the neighborhood of these points E_k can be presented as $E_k = -\Delta + p_{\parallel}^2/2m_{\parallel} + p_{\perp}^2/2m_{\perp}$, where near $(\pi/2, \pi/2)$, $p_{\parallel} = (k_x - k_y)/2$, $p_{\perp} = (k_x + k_y)/2$. Self-consistent calculations predict that at large U both masses scale as inverse bandwidth $J = 4t^2/U$, but numerically, $m_{\parallel}$ (which is infinite in the mean-field theory) is several times larger than $m_{\perp}$.

We now turn to the description of our calculations. Consider first a Néel ordered state at small but finite doping. Near $\mathbf{Q}_0 = (\pi, \pi)$, the static transverse susceptibility should

have a hydrodynamic form [15] $\chi_{\text{st}}^{xx}(\mathbf{q} \approx \mathbf{Q}_0) = \mathbf{N}_0^2/(\rho_s(\mathbf{q} - \mathbf{Q}_0)^2)$, where $\mathbf{N}_0$ is the on-site magnetization, and ρ_s is the spin-stiffness. This form of transverse susceptibility is reproduced in the RPA formalism by summing up the ladder series of bubble diagrams. At half-filling, only bubbles containing valence and conduction fermions are allowed, while at finite doping chemical potential moves inside the valence band, and one also has contributions to χ from bubbles with only valence fermions. These last contributions are proportional to 2D Pauli susceptibility, which, as we said, does not depend on carrier concentration. As a result, one obtains a finite correction to the spin stiffness already at a very small doping [11]:

$$\rho_s = \rho_s^0(1 - z), \quad z = 4T\chi_{2\text{D}}^{\text{pauli}} = \frac{2T\sqrt{m_\perp m_\parallel}}{\pi} \quad (2)$$

Here ρ_s^0 is the spin stiffness at half filling, and T is the scattering amplitude for two holes. The latter is equal to U in the mean-field description, but strong self-energy and vertex corrections reduce T to the order of the bandwidth J [2,11,16], which in turn implies that z is simply a dimensionless number. For the rest of the paper, we will consider z as a phenomenological input parameter [17]. It follows from (2) that Néel state remains stable at finite doping if $z < 1$, but becomes unstable if $z > 1$, which implies that we have to consider incommensurate spin configurations as possible candidates for the ground states.

Let us first focus on the two simplest candidates [2,6,18]: the spiral states with the ordering vectors (π, Q) and (Q, Q) . For definiteness, we choose the ordering to be in the XY plane such that $S_R^X = S_{\bar{Q}} \cos(\bar{\mathbf{Q}}\mathbf{R})$, and $S_R^Y = S_{\bar{Q}} \sin(\bar{\mathbf{Q}}\mathbf{R})$, where $\bar{\mathbf{Q}}$ is the ordering momentum.

The mean-field analysis for the incommensurate states proceed in the same way as for the Néel state. We skip the details of the calculations and focus only on the results. For (π, Q) state, we obtained $Q = \pi - (U/t)x$ and

$$E^{(\pi, Q)} - E^{(\pi, \pi)} = \frac{\pi x^2}{4\sqrt{m_\perp m_\parallel}}(1 - z) \quad (3)$$

Clearly, the (π, Q) phase has lower energy than the (π, π) phase for $z > 1$, exactly where the susceptibility of the (π, π) state becomes negative.

For (Q, Q) phase, the inverse pitch Q is the same, but the energy difference is

$$E^{(Q,Q)} - E^{(\pi,\pi)} = \frac{\pi x^2}{4\sqrt{m_\perp m_\parallel}}(3 - 2z) . \quad (4)$$

Comparing (3) and (4), we observe that the (π, Q) spiral phase has the lowest energy at $1 < z < 2$. This is roughly consistent with the results of other mean-field approaches [2,5]. At $z > 2$, the (Q, Q) state has the lowest energy. However, we found that $\partial E^{(Q,Q)}/\partial x^2$ is negative at $z > 2$. This suggests phase separation which is probably unphysical because the model neglects long-range Coulomb interaction [2]. In view of this, we will only consider the case $1 < z < 2$.

We now turn to the central topic of our paper, which is the study of collective bosonic excitations (poles of dynamical susceptibility) in the (π, Q) spiral phase. The $SO(3)$ symmetry of spin rotations is completely broken in the spiral phase, and one, therefore, should expect to have three bosonic zero modes with two different spin-wave velocities. The calculations of the susceptibilities is straightforward but lengthy because we have to solve a set of four coupled Dyson equations. For in-plane (XY) spin fluctuations, a simple symmetry analysis predicts that the zero modes are located at $\mathbf{q} = \mp \bar{\mathbf{Q}}$ for χ_q^{+-} and χ_q^{-+} correspondingly. We indeed found that at $\tilde{\mathbf{q}} = (\mathbf{q} + \bar{\mathbf{Q}}) \ll 1$, static χ_q^{+-} has the form: $\chi_q^{+-} = 2/(J\tilde{\mathbf{q}}^2(2 - z))$, i.e., it is *positive* for $z < 2$. For the dynamical susceptibility, we found a pole at $\omega = c\tilde{q}$ with the same c (up to $O(x)$ terms) as at half filling. This is in agreement with other results [10,18].

We now turn to the magnetic susceptibility χ_q^{zz} associated with the fluctuations of the plane of spin ordering. This channel is coupled to the charge and in-plane spin fluctuations only dynamically, so for the full static susceptibility one has the simple RPA formula $\chi_q^{zz}(\omega = 0) = \bar{\chi}_q^{zz}(\omega = 0)/(1 - U\bar{\chi}_q^{zz}(\omega = 0))$ where $\bar{\chi}^{zz}$ is the bare bubble. From general symmetry considerations, we would expect the Goldstone modes in χ_q^{zz} to be at $\mathbf{q} = \pm \bar{\mathbf{Q}}$. Performing calculations to the lowest nontrivial order in the density (i.e., to $O(x^2)$), we have, indeed, found that $(\chi_q^{zz})^{-1}$ at $\mathbf{q} = \pm \bar{\mathbf{Q}}$ is equal to zero. However, with the same accuracy, we also found that the stiffness for excitations near these momentum is equal to zero, which in turn means that to order $O(x^2)$, all fluctuation modes between $\bar{\mathbf{Q}}$ and $-\bar{\mathbf{Q}}$, including

the mode at (π, π) , remain degenerate and gapless. A similar degeneracy was found in the macroscopic consideration by Shraiman and Siggia [10]. They further assumed that $O(x^3)$ terms make the spin stiffness at $\pm\bar{\mathbf{Q}}$ positive. This scenario yields anomalously small spin-wave velocity for out-of-plane fluctuations, $v \propto \sqrt{x}$, susceptibility at $(\pi, \pi) \propto x^{-3}$, and the doping-dependent quantum corrections to the order parameter which scale as $\sqrt{x}$ instead of x .

We, however, calculated the static susceptibility χ^{zz} at $\mathbf{q} = (\pi, \pi - \tilde{q})$ explicitly to the order x^3 and found after tedious algebra:

$$(\chi^{zz})_q^{-1} = \frac{4x^3}{U} \left(1 - \frac{2}{z}\right) \left(1 - \frac{\tilde{q}^2}{\bar{q}^2}\right) \quad (5)$$

where $\bar{q} = \pi - Q$. We see that while the Goldstone mode at $\tilde{q} = \pm\bar{q}$ survives to order $O(x^3)$ (as it should), the static susceptibility for out-of-plane fluctuations at and near (π, π) is *negative* for $z < 2$, where mean-field solution favors (π, Q) phase. This implies that the spiral (π, Q) state is unstable at low doping. Note that all $O(x^3)$ terms come from the integration within the hole pockets (the bubbles with conduction and valence fermions yield regular corrections in powers of x^2). Near the minima, the hole spectrum has a quadratic dispersion for an arbitrary form of the hopping term, and we therefore expect eqn. (5) to be valid also for the models with further-neighbor hopping, etc.

We now address the issue of the true ground state at finite doping. The instability in χ^{zz} at (π, π) , implies that the system prefers to have a spontaneous commensurate antiferromagnetic order along Z direction in addition to the incommensurate spin ordering in the XY plane. This gives a set of magnetic states which are all noncoplanar (and therefore have nonzero chirality), and differ in the ratio between the order parameter amplitudes along Z direction and in the XY plane, Fig.1. Let us first calculate the ground state energies for this set of states. Clearly, we have to introduce two gaps $\Delta_{\perp} = U\langle S_{\perp} \rangle$, and $\Delta_{\parallel} = U\langle S_{\parallel} \rangle$, where $\langle S_{\perp} \rangle$ and $\langle S_{\parallel} \rangle$ are the magnitudes of the off-plane and in-plane components of the order parameter, respectively. Performing the mean-field decoupling and the diagonalization of the Hubbard Hamiltonian, we obtained after some algebra

$$E_{\Delta_{\perp}} = E_{\Delta_{\perp} \rightarrow 0} - Ux^3 \left(\frac{\Delta_{\perp}}{\Delta_{\parallel}} \right)^2 \left[\frac{2}{z} - 1 \right] \quad (6)$$

where $E_{\Delta_{\perp} \rightarrow 0}$ is the ground state energy in the limit when the Z -component of order parameter tends to zero, and the total order parameter $\Delta^2 = \Delta_{\perp}^2 + \Delta_{\parallel}^2$ is fixed by the self-consistency conditions, $\Delta \approx U/2$ [19]. It is apparent from (6) that the energy *decreases* as the ratio $\Delta_{\perp}/\Delta_{\parallel}$ increases. Notice that (i) the energy dependence on the ratio of Δ is in the order $O(x^3)$, while to order x^2 , all states from the set are degenerate in energy, and (ii) the r.h.s. of (6) contains the same positive factor $(2/z) - 1$ as the expression for χ^{zz} at (π, π) . The inverse pitch of the spiral is related to x by the requirement that the two self-consistency conditions for two order parameters be compatible with each other. We obtained ($\bar{q} = \pi - Q$)

$$\bar{q} = \frac{U}{t} \frac{\Delta}{\Delta_{\parallel}} x \left[1 + 2x \left(1 - \frac{\Delta^2 + \Delta_{\parallel}^2}{2\Delta_{\parallel}^2} \frac{2}{z} \right) \right]. \quad (7)$$

As written, Eqn. (6) is valid when $\bar{q} \ll \Delta_{\parallel}/\Delta$. Since $\bar{q}\Delta_{\parallel} \sim x$ (see (7)), we can keep lowering the energy by decreasing $\Delta_{\parallel}$ as long as $\Delta_{\parallel} \gg \sqrt{x}$. When both $\Delta_{\parallel}$ and $\bar{q}$ become of the order of $\sqrt{x}$, $\Delta E = E_{\Delta_{\perp}} - E_{\Delta_{\perp} \rightarrow 0}$ has a more complicated form:

$$\Delta E = \frac{Ux^2}{2} \left[1 + (\alpha^2 + 2)\beta^2 - \frac{\beta z}{6} \left(\left(\alpha^2 + \frac{8}{z} \right)^{3/2} - \alpha^3 \right) \right]$$

Here we introduced $\Delta_{\parallel} = \alpha\Delta x^{1/2}$, $\bar{q} = \beta(U/t)x^{1/2}$. Eqn (7) relates α and β as: $\beta = z((\sqrt{\alpha^2 + 4/z} - \alpha)/2)$. Minimizing now the energy with respect to α we obtain to the lowest order in $2 - z$: $\alpha \approx \sqrt{7z/(12(2 - z))}$, $\beta \approx 1/\alpha$, and

$$\Delta E = -\frac{Ux^2}{2} \left[\frac{12}{7} \left(1 - \frac{2}{z} \right)^2 \right] \quad (8)$$

As expected, ΔE is negative. Observe also that it scales as x^2 , instead of x^3 as in (6). Clearly then, the equilibrium state with $\Delta_{\parallel} \sim \sqrt{x}$ does not belong, strictly speaking, to a set of initially degenerate spin configurations, and could be selected already in the calculations to order $O(x^2)$. The discovery of the degenerate set of states and of the instability of the planar spiral however gave us a hint where to look for the global minimum of the energy.

Consider next the magnetic susceptibility of the equilibrium state. By virtue of having minimum energy it has a positive static susceptibility diverging only at the Goldstone points.

We also found that noncoplanar ordering gives rise to a strong mixture between in-plane and out-of-plane fluctuations, such that the Goldstone modes in χ_q^{zz} at $\mathbf{q} = \pm\bar{\mathbf{Q}}$ give rise to a static zero mode in χ_q^{+-} at (π, π) . Another zero mode in $\chi^{+-}(q)$ corresponds to the spin rotation about the Z axis, and appears at $\mathbf{q} = -\bar{\mathbf{Q}}$, as in the spiral case. Overall, the in-plane static susceptibility χ^{+-} has two poles

$$\chi^{+-}(\mathbf{q}) \approx \frac{\chi_\pi}{(\mathbf{q} - \bar{\pi})^2} + \frac{\chi_{\bar{Q}}}{(\mathbf{q} + \bar{\mathbf{Q}})^2} , \quad (9)$$

where the residues χ_π and $\chi_{\bar{Q}}$ are proportional to $\Delta_\perp^2$ and $\Delta_\parallel^2$ respectively. Because $\Delta_\parallel \sim \sqrt{x}$, the residue of the pole at the incommensurate wave vector $q = -\bar{\mathbf{Q}}$ is proportional to the hole concentration, and is suppressed with respect to the pole at the commensurate wave vector (π, π) . We also considered dynamical susceptibility and found that the spin wave velocity in the zz channel does not contain any smallness in x . However, when $z \approx 2$, it behaves as $c \sim ((2/z) - 1)$.

To summarize, we studied in this paper the magnetic phases of the 2D Hubbard model at low doping. We found that the planar spiral (π, Q) phase has lower energy than the Néel and (Q, Q) phases in some range of a phenomenological parameter z . However, this state has a negative static susceptibility in a region of q space around (π, π) , and is therefore unstable. We searched for the stable state, and found that it corresponds to a very different noncoplanar spin configuration. This, in turn, gives rise to a novel scenario of the transformation of the equilibrium magnetic state with doping. Namely, upon doping, the initial commensurate antiferromagnetic ordering remains unchanged except for a small decrease in the amplitude of the order parameter. At the same time, doping gives rise to a transverse component of the order parameter which forms a spiral in the plane perpendicular to the direction of commensurate order. This transverse component is small to the extent of x , and the low- T behavior at finite doping remains nearly the same as in the commensurate antiferromagnet [20].

Finally, we discuss how these results can be applied to the experimentally studied disordered regions of cuprate superconductors. The hope here is that the strongest divergence in

the susceptibility in the ordered state corresponds to the maximum value of the peak in χ in the region where the correlation length is finite. In the absence of a long-range order, the actual susceptibility is a mixture of χ^{+-} and χ^{zz} . In the spiral state, both χ^{+-} and χ^{zz} had peaks at the incommensurate momenta $\pm\bar{\mathbf{Q}}$. In the noncoplanar state however, the peak in χ at the commensurate (π, π) point is much stronger than at the incommensurate momenta. We thus observe that although incommensurability in the nonplanar state is much larger than in the spiral state (inverse pitch of the spiral scales as $\sqrt{x}$), experimentally it is very difficult to distinguish the noncoplanar state from the Néel state. The noncoplanar state therefore should yield the same T -dependence of spin-lattice relaxation rate as the (π, π) phase. This is consistent with the low-frequency NMR experiments [8]. The situation at higher frequencies (where neutron-scattering experiments were done [7]) is less clear as high-frequency bosonic excitations in the spiral phase are positive, and this phase may be advantageous over noncoplanar state. The possibility of the frequency crossover between the two phases is now under study. Note in passing that for $U \sim 6t$ relevant to experiments, we obtain $q \approx 6x$ for the planar spiral state in a striking agreement with neutron scattering experiments on $La_{2-x}Sr_xCuO_4$ [7] which yield $q/\pi \approx 2x$.

It is our pleasure to thank A.Abanov, V. Barzykin, R.Joynt, D. Pines, S. Sachdev and A. Sokol for useful discussions. The work was supported by the University of Wisconsin-Madison Graduate School and Electric Power Research Institute.

REFERENCES

- [1] P. Montoux, A. V. Balatsky, and D. Pines, Phys. Rev. Lett. **67** (1991)
- [2] B. I. Shraiman and E. D. Siggia, Phys. Rev. Lett. **62**, 1564 (1989);
- [3] H. J. Schulz, Phys. Rev. Lett. **64**, 1445 (1990)
- [4] S. John and P. Voruganti, Phys. Rev. B **43**, 10815 (1991); S. John, P. Voruganti, and W. Goff, Phys. Rev. B **43**, 13365 (1991).
- [5] a) C. Jayaprakash, H.R. Krishnamurthy and S. Sarker, Phys. Rev B **40**, 2610 (1989); b) B. Chakraborty et al, Phys. Rev. B **41**, 2653 (1990).
- [6] S. Sachdev, Phys. Rev B **49**, March (1994).
- [7] S-W Cheong et al, Phys. Rev. Lett., **67**, 1791 (1991).
- [8] L. Reven et al, Phys. Rev B **43**, 10466 (1991); R. E. Walstedt, B.S. Shastry and S-W. Cheong, unpublished; D. Pines, private communication.
- [9] J. R. Schrieffer, X. G. Wen, S. C. Zhang, Phys. Rev. B **39**, 11663 (1989)
- [10] B. I. Shraiman and E. D. Siggia, Phys. Rev. B **46**, 8305 (1992).
- [11] A. V. Chubukov and D. M. Frenkel, Phys. Rev. B **46**, 11884 (1992).
- [12] A. Singh and Z. Tešanović, Phys. Rev B **41**, 614 (1990); A. Singh, Z. Tešanović and Ju. H. Kim, Phys. Rev B **44**, 7757 (1991).
- [13] G. Vignale and M. R. Hedayati, Phys. Rev. B **42**, 786 (1990); E. Dagotto et al, Phys. Rev B **41**, 9049 (1990); A. V. Chubukov and K. A. Musaelian, Phys. Rev B, submitted.
- [14] S. Trugman, Phys. Rev B **37**, 1597 (1988); S. Sachdev, Phys. Rev. B **39**, 12232 (1989); M. Boninsegni and E. Manousakis, Phys. Rev B **43**, 10353 (1991).
- [15] B.I. Halperin and P. Hohenberg, Phys. Rev. B **177**, 952 (1969).

- [16] C. L. Kane, P. A. Lee, and N. Read, Phys. Rev. B **39**, 6880 (1989).
- [17] Actually, the scattering amplitude of a 2D Fermi gas is logarithmically singular in the limit of very low densities: $T = U_{\text{eff}}/[1 + (mU/4\pi) \log(mU_{\text{eff}} p_F/4\pi)]$, where U_{eff} is the effective interaction (of the order of the bandwidth), and $m = \sqrt{m_{\perp} m_{\parallel}}$. This always makes the collinear antiferromagnetic state stable at *very* low doping [11]. However the range of doping where logarithmic corrections are important is probably very small, and in this paper we simply set $T = U$.
- [18] J. Gan, N. Andrei and P. Coleman, J. Phys. Cond. Matter **3**, 3537 (1991).
- [19] In fact, there is a small discontinuity ($\sim x^3$) in the ground state energy at $\Delta_{\perp} \rightarrow 0$ because at any finite $\Delta_{\perp}$ the value of the inverse pitch of a spiral comes from the compatibility of the two self-consistency equations rather than from the minimization of energy. This complication is irrelevant to our analysis as the true ground state has the energy difference with the planar spiral state much larger than the jump at $\Delta_{\perp} \rightarrow 0$.
- [20] S. Chakravarty, B.I. Halperin and D. Nelson, Phys. Rev. B **39**, 23334 (1989); A. Chubukov, S. Sachdev and J. Ye, Phys. Rev B **49**, May (1994); A. Chubukov and S. Sachdev, Phys. Rev. Lett **71**, 169, 3615 (1993).

FIGURES

FIG. 1. a) Spin configuration of a noncoplanar state. Arrows with thick ends point out of the plane, while those with thick tails — into the plane. This configuration is different from the double spiral considered in [5]b. b) Two adjacent spins in the equilibrium configuration. The in-plane component, $S_{\perp} \sim x^{1/2}$, is small compared to the off-plane component, $S_{\parallel}$.